

Eidorff dentals legering certifikater

BEGO
Wirobond® 280

Standard analysis, % by weight (elements)

Co	60.2	W	6.2
Cr	25.0	Ga	2.9
Mo	4.8	Si, Mn	

CE 0197
 ISO 9693 / ISO 22674

CE 0483

Heracus Kulzer
 Laboratory Products Division

Keramikgold PKF

Type	Gold casting alloy / extra high strength DIN EN ISO 1562-3										
Colour	Composition in mass %										
yellow	Au	Ag	Pt	Ta	Zn	Rh	Ir				±=0.1%
	75.0	12.5	9.0	0.45	2.0	1.0	x				

CE 0483

Heracus Kulzer
 Laboratory Products Division

Maingold® SG

Type	Gold casting alloy / extra high strength DIN EN ISO 1562-4										
Colour	Composition in mass %										
yellow	Au	Ag	Pt	Pd	Cu	Zn	Ir	Ru			±=0.1%
	71.0	12.3	2.0	1.0	12.2	0.5	x	x			